

PERMOHONAN PERSETUJUAN MATERIAL

Aplikasi Consol Floor 351 Ecocrete

Nama Proyek	: Epoxy Flooring Area Shelter (Outdoor) PT. Mustika Lastari Jaya di Lanud Madiun
Nomor SPK	: 009/PO/MLJ/I/2026
Lokasi Pekerjaan	: Area Shelter Lanud Madiun
Item Pekerjaan	: Aplikasi Consol Floor 351 Ecocrete
Tanggal Pengajuan	: 23 Juli 2026
Diajukan Oleh	: Andi Ahmad Raga

1. MATERIAL YANG DIAJUKAN

1.1.

Nama Produk	: Consol Primer Hybrid Epoxy	
Packaging	: 5.4 kg/set	
Keterangan	: Consol Primer Hybrid berfungsi sebagai primer untuk memperkuat bonding.	

1.2.

Nama Produk	: Consol Floor 351 Ecocrete T4	
Packaging	: 30,6 kg / set	
Keterangan	: Digunakan untuk coating repair dan maintenance lantai aplikasi Consol Floor 351 Ecocrete	

2. LEMBAR PERSETUJUAN

Diajukan Oleh	Diperiksa Oleh	Disetujui Oleh
(Andi Ahmad Raga)	(_____)	(_____)
Tanggal: _____	Tanggal: _____	Tanggal: _____



CONSOL PRIMER HYBRID EPOXY

Water Based Epoxy Primer

DESCRIPTION

CONSOL PRIMER HYBRID EPOXY is two components, water based epoxy and solvent free. The system is formulated to bind to damp, dry, and green concrete.

RECOMMENDED FOR

CONSOL PRIMER HYBRID EPOXY can be used as primer and adhesion promoter for epoxy and polyurethane floor on:

- Concrete floors
- Cementitious Mortar Screed
- Epoxy Cement Floor
- Epoxy Mortar Floor
- Epoxy Concrete Floor

BENEFITS

CONSOL PRIMER HYBRID EPOXY provides the following beneficial properties such as:

- Low viscosity
- Solvent free
- Low odour
- Excellent bonding strength
- Water based
- Excellent adhesion to dry, damp, green concrete

COVERAGE

Material consumption approx. 0.15 - 0.3 kg/m² depends on substrate conditions

PRODUCT DATA

Form

Liquid

Colour

Part A : Milky white, liquid

Part B : Green to brown, liquid

Density

Part A : 1.05 kg/L

Part B : 1.05 kg/L

Bond Strength

1.5 N/mm² (Failure on concrete)

Pot Life (30°C)

Approx. 20 minutes

Storage

Dry, cool, shaded place

Shelf Life

1 years if stored in unopened original container

Packaging

Part A : 2.1 kg

Part B : 3.3 kg

INSTRUCTION FOR USE

Substrate Condition

Surfaces must be structurally sound, clean, and free from loose particles, oil, grease, and all other contaminants. The compressive strength of the substrates shall not be less than 20 N/mm² and the bond strength of the substrate must be at least 1.5 N/mm².

Surface Preparation

Remove oil, grease, and wax contaminants by scrubbing with industrial grade detergent or degreasing compounds followed by mechanical cleaning. Cement laitance, loose particles, mould release agents, curing membrane and other contaminants must be removed from the surface by shot blasting, scarifying or grit-blasting followed by vacuum cleaning.

Mixing

As Primer

Mixing use a low speed (300 rpm) electric mixer, mix part A&B for at least 3 minutes until the mix is uniform.

Mixing Ratio:

General primer : **A : B = 2.1 : 3.3**



APPLICATION

As Primer

Apply **CONSOL PRIMER HYBRID EPOXY** by squeegee or brush on to the prepared surface.

If the surface has moisture barrier, allow the moisture barrier to dry before apply **CONSOL PRIMER HYBRID EPOXY**.

Curing:

At 30 °C, foot traffic access in 6 hours, fully cured in 48 hours.

PRECAUTIONS

- **CONSOL PRIMER HYBRID EPOXY** contain certain chemicals which can cause skin irritation if exposed and respiratory reaction if inhaled.
- Keep away from open light, including welding.
- Avoid contact with skin and eyes.
- If skin contact occurs, wash skin thoroughly.
- Wear protective glove and eye protection during work.
- If in eyes, hold eyes open, flood with warm water and seek medical attention without delay.
- Not classified as finishing material, and slightly color difference on result may occurred.

Head Office
Ruko Wadungasri Permai Blok B 8
Jl. Wadungasri 46-48 Waru-Sidoarjo
Telp. 031-8661122 - Fax. 031-99004958

Branch Office
Kawasan Industri Lippo Cikarang II
Delta Silicon 5, Jl. Daru III, Blok G5, No. 53
Cicau, Bekasi, Jawa Barat 17530
Telp. 021-89914905

Factory
Kompleks Industri dan Pergudangan
Golden Blok B16-17
Jl. Industri II Tambak Sawah, Waru-Sidoarjo



**KIMIA
KONSTRUKSI
INDONESIA**